


DALFRATHERM[®]-1200 ULS BULK

Technical data sheet



Product description

ULS-grade wool is manufactured by spinning a high purity blend of carefully selected raw materials. In addition to the enhanced thermal properties, large shot particles have been significantly reduced. This makes the fiber soft to touch and it causes less skin irritation during handling.

DALFRATHERM[®]-1200 ULS meets the requirements specified under NOTE Q of European Regulation 1272/2008. All DALFRATHERM[®] ULS fiber products are therefore exonerated from labelling requirements in Europe.

TECHNICAL DATA

Grade		AES
Colour		white
Classification temperature	°C	1200
Continuous use temperature	°C	1050
Beaker value (fibre length)		
Chopped	ml	100
Short		300
Long		700
Mean Fibre Diameter	µm	2 - 4
Shot Content (JetSieve)	> 45µm	<35%
Chemical composition (GB/T 21114)		
SiO ₂	%	63-68
CaO	%	26-33
MgO	%	3-7
Others	%	<0.8

DELIVERY SIZES

Different Bulk Types

Lubricated	used for yarn/ textile, joint filler
Unlubricated	used for mastics, vacuum forming

Different Bulk Styles

Chopped	used for high density VF shapes, mastics	(18 kg/bag)
Short	standard VF manufacturing and mastics	(15 kg/bag)
Long	void/joint fillers, dry injected fibers and textiles	(12 kg/bag)

DALFRATHERM® -1200 ULS Bulk is supplied in plastic bags on pallets to maximize the quantity per container. Not all types and styles are available as standard

Application area

- Raw material for Vacuum Forming proces
- Raw material for insulating castables, mastics and coatings
- Filling and stuffing of voids and gaps in furnace lining
- Injected/blown fibre in double wall chimneysand
- Long fibres for yarn production (textiles)
- General technical insulation of furnaces and technical installations

Yield

In many applications the effect of shot in bulk fibre is underestimated. In Vacuum Forming and Mastic making the shot is typically sinking in the liquid mixture, resulting in less volume per kg of bulk fibre. With the Ultra Low Shot technology we typically improve the yield by 15-30 % compared to previous generations.

Working & processing

The filling of cavities for heat insulation can be carried out with DALFRATHERM®-1200 ULS bulk. The material is easy to plug and should be compressed to approximately half of the initial volume (approx. 130 kg/m).

Dust is produced during procession. Dust can be harmful to the health. Avoid contact with eyes and skin. Do not breathe in the dust. Dust should be removed by suction. The dust limits are to be adhered to. See product safety data sheet.

Properties & benefits

- Proven technical solution
- Low shot technology
- Higher yield in secondary processing
- Excellent insulation performance
- High handling strength
- Excellent thermal stability
- Resistant to thermal shock

Sustainability

Our world has changed in the past few decades with reduced CO2 emissions and energy consumption as the key drivers. Therefore focus must be on the most effective methods of saving energy.

A high performance insulation lining (such as DALFRATHERM) for the technical installation not only saves energy but also provides energy bill savings, avoids heat loss and demands less power.

All specified technical data are mean values from the production which are subject to the usual fluctuations and do not represent guaranteed properties in the sense of a guarantee. All information corresponds to the current state of the art and has been presented and described to the best of our knowledge. Changes due to new findings are possible, errors and misprints are not excluded. With regard to any liability, our delivery and payment terms apply exclusively. Request safety datasheet. With the publication of this edition, all previously published datasheets are invalid. © Copyright Etex NV, Brussels, Belgium. All rights reserved. 2022-01

Etex Industry c/o Microtherm N.V., Industriepark-Noord 1, 9100 Sint-Niklaas, Belgium | T +32 (0)3 760 19 80 | F +32 (0)3 760 19 99
industry@promat.com | www.promat.com/industry